

REPORT DOCUMENTATION PAGE			Form Approved OMB NO. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comment regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE 1/30/96		3. REPORT TYPE AND DATES COVERED Final Report 6/15/92-10/31/95
4. TITLE AND SUBTITLE Pyrometallurgical, Physical, and Mechanical Behavior of Weldments			5. FUNDING NUMBERS DAAL03-92-G-0270	
6. AUTHOR(S) David L. Olson and Robert H. Frost				
7. PERFORMING ORGANIZATION NAMES(S) AND ADDRESS(ES) Colorado School of Mines Center for Welding, Joining, and Coatings Research Metallurgical and Materials Engineering Golden, CO 80401-1887			8. PERFORMING ORGANIZATION REPORT NUMBER MT-CWJCR-096-004	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) U.S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709-2211			10. SPONSORING / MONITORING AGENCY REPORT NUMBER ARO 30060-18MS	
11. SUPPLEMENTARY NOTES The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.				
12a. DISTRIBUTION / AVAILABILITY STATEMENT Approved for public release; distribution unlimited.			12b. DISTRIBUTION CODE 19960621 120	
13. ABSTRACT (Maximum 200 words) This research program aimed to achieve a better understanding of pyrometallurgical reactions during welding and process-microstructure correlations. The validity of proposed mechanisms for the formation of weld metal acicular ferrite was tested by using selected surrogate additions with similar chemical behavior but different physical properties compared to titanium-boron additions known to promote acicular ferrite formation. The results suggest that inclusion density and size distribution are the most important factors in acicular ferrite formation. The evolution of inclusions in the weld pool during welding and solidification was modeled. Procedures are reported for the use of shielding gas oxygen content as a welding parameter to optimize weld metal microstructure and properties. Exothermically-assisted shielded metal arc welding consumables were evaluated as a possible means to substitute chemical energy for traditional electrical energy during welding. Exothermic reactions produced up to 40 pct. of the heat required for welding. The influence of electrochemical reactions during welding on weld metal composition was investigated. Evidence of electrochemical behavior in specific welding parameter ranges was found. A search for new non-destructive evaluation techniques and associated procedures to measure specific weld metal compositions or constituents was undertaken. As a demonstration, magnetic property measurements were used to detect phase transformations in Al-Cu alloys.				
14. SUBJECT TERMS Welding Pyrochemistry, Process-Microstructure Correlations, Exothermically-Assisted Welding Consumables, Acicular Ferrite, Electronic and Magnetic Phase Detection, Structure Evolution			15. NUMBER OF PAGES 14	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OR REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

MT-CWJCR-096-004

PYROMETALLURGICAL, PHYSICAL, AND
MECHANICAL BEHAVIOR OF WELDMENTS

Final Report

David L. Olson and Robert H. Frost

January 31, 1996

U.S. Army Research Office

DAAL03-92-G-0270

Colorado School of Mines

Approved for Public Release;

Distribution Unlimited

4A. STATEMENT OF THE PROBLEMS STUDIED

This research program aimed to achieve a better understanding of pyrometallurgical reactions during welding and process-microstructure correlations. The validity of proposed mechanisms for the formation of weld metal acicular ferrite was tested by using selected surrogate additions with similar chemical behavior but different physical properties compared to titanium-boron additions known to promote acicular ferrite formation. The results suggest that inclusion density and size distribution are the most important factors in acicular ferrite formation.

The evolution of inclusions in the weld pool during welding and solidification was modeled. Procedures are reported for the use of shielding gas oxygen content as a welding parameter to optimize weld metal microstructure and properties. Exothermically-assisted shielded metal arc welding consumables were evaluated as a possible means to substitute chemical energy for traditional electrical energy during welding. Exothermic reactions produced up to 40 pct. of the heat required for welding. The influence of electrochemical reactions during welding on weld metal composition was investigated. Evidence of electrochemical behavior in specific welding parameter ranges was found. A search for new non-destructive evaluation techniques and associated procedures to measure specific weld metal compositions or constituents was undertaken. As a demonstration, magnetic property measurements were used to detect phase transformations in Al-Cu alloys.

4B. SUMMARY OF THE MOST IMPORTANT RESULTS

Research efforts during this contract have concentrated on: (1) the influence of Zr-Al and Ti-B additions on the formation of weld metal acicular ferrite; (2) the prediction of the nature and formation sequence for nonmetallic inclusions in the weld metal; (3) the use of shielding gas oxygen as a welding parameter; (4) the development of exothermically assisted welding consumables; (5) the influence of electrochemical reactions on arc welding processes with a plasma electrolyte; and (6) the use of electric and/or magnetic detection and characterization of weld metal microstructure. The research activities are to achieve a better understanding of the pyrometallurgical reactions occurring during welding and to establish a better understanding of process-microstructure correlations.

Zr-Al and Ti-B Additions:

A project evaluating the various proposed mechanisms for the formation of weld metal acicular ferrite, the desired high toughness-higher strength microstructure, was completed. By using surrogate additions the research found that low ferrite-inclusion lattice mismatch is not a primary factor as suggested by other investigations [1B-7B]. The important factor in controlling the weld metal microstructure, and thus the properties, was found to be the inclusion number density and size distribution [8B-11B]. The work indicated that Zr-Al microadditions to the weld pool can achieve the same weld metal microstructure and properties as commercially-used Ti-B microadditions. Zirconium was selected to replace titanium because it is chemically similar to titanium but has oxides with very different lattice mismatch compared to ferrite. Aluminum was selected to replace chemically similar boron to allow comparisons of their results. In small

concentrations, aluminum behaves like boron. The substitution of zirconium and aluminum for titanium and boron thus allowed evaluation of the validity of various models for the microstructural evolution of weld metal microstructure. Since the results suggested that inclusion density and size distribution are primary factors, it became apparent that inclusion evolution needs to be thoroughly understood in order to establish new effective ways to formulate high performance welding consumables.

Sequence of the Evolution of Inclusions:

A precipitation sequence model was developed which used the free energy of formation of various oxides and a model for microsegregation of alloy elements and oxygen during weld solidification to predict the location (weld pool or interdendritic) and the order in which the inclusions formed [12B, 13B]. For aluminum-killed steel with titanium microadditions this model predicts that aluminum oxide inclusions will be the first to precipitate and that these inclusions will continue to form during the initial stages of solidification. Ti_2O_3 and Ti_3O_4 inclusions will form near the end of solidification, and manganese and silicon oxides will only form during the final stages of solidifications. The sequence of oxide formation, when considering both the various temperatures of oxide formation and the interdendritic microsegregation, was found to explain the often observed bimodal size distribution. The larger inclusions result from the primary deoxidation, the role of the aluminum addition; and the much smaller inclusions result from the compositional perturbations found in the interdendritic regions and from the much lower formation temperature common to the interdendritic regions. The work suggests that weld metal microstructural optimization will result from proper selection of alloy additions and specifically selected shield gas oxygen content.

Shielding Gas Oxygen Content as a Welding Parameter:

An investigation was performed on microalloyed steels to demonstrate that weld metal microstructures can be altered by small shifts in the shielding gas oxygen content. The results showed that weld metal microstructure and properties can be optimized by use of simple metallographic determination of the fractions of the various forms of weld metal ferrite for a specific shielding gas oxygen content [14B-16B]. The shielding gas oxygen content can then be varied by a known amount to achieve a more desirable weld metal microstructure. The relationship between weld metal oxygen content and the oxygen or carbon dioxide content in the shielding gas was determined. The work furthered the predictability of weld metal microstructure and properties by developing a modified P_{cm} alloying index to include weld metal oxygen content [17B]. This index is called the P_{cmo} .

Exothermically Assisted Welding Consumables

The possibility of producing a chemically self-heating welding electrode was investigated. A liquid nitrogen calorimeter was used to study the heating effects of exothermic additions to flux-coated welding consumables during shielded metal arc welding. The calorimetry data was studied in conjunction with weld bead area measurements to correlate the heating effect with the melting of the base plate and electrode. The exothermic additions evaluated consisted of aluminum/hematite, magnesium/hematite, and aluminum/magnesium/hematite mixtures. All three types of additions were found to increase the amount of heat transferred to the work piece. Exothermic reactions produced up to 40 percent of the total heat required for shielded metal arc welding.

This investigation has shown that exothermic welding consumables can assist in heat generation and electrode melting [18B]. Aluminum additions are significantly more effective than magnesium in melting the electrode and weld bead, and in promoting increased penetration of the base plate. Magnesium is less effective in supplying heat because its reaction rate is high compared to the rate of electrode melting. The resultant prematurely-evolved heat cannot be transferred effectively to the base plate. It is desirable to have most of the exothermic reactions occur in the molten electrode tip, and to transfer the heat to the base plate via the molten droplets. The relationship between the rate of the exothermic reaction and the melting rate of the electrode determines the overall efficiency of the process.

Present efforts have progressed from shielded metal arc welding to evaluation of the use of cored wires that contain exothermic additions. The cored wire consumables should increase the thermal efficiency of the process and allow for more of the required heat to be generated by chemical reactions. The use of cored wires to achieve exothermic assisted welding consumables will be continued with a follow-up ARO contract (DAAH04-95-1-0135). A strip-to-cored wire mill has been procured and is being set up for experimental cored wire production.

Influence of Electrochemical Reactions during Welding:



Efforts to determine the influence of electrochemical reactions have investigated reactions involving the plasma in the shielded metal arc welding process [19B-23B]. During shielded metal arc welding current is transferred across both the plasma-metal and slag-metal interfaces. The charge carriers in the plasma include electrons and positively ionized atoms, but negative ions such as those found in molten slag conductors are not available. Composition changes at the

plasma-metal interface are controlled by the nature of the charge carriers in the plasma and by vaporization from the metal surface to the plasma.

Direct current shielded metal arc welds were made on a copper plate in both DCEP and DCEN polarities. The nature and extent of electrochemical reactions were investigated as a function of polarity, current, and weld travel speed by chemical analysis of the weld bead, the electrode tip and of the metal droplets. The compositional changes in these specimens provided information on the electrochemical and thermochemical processes at the electrode, on the thermochemical reactions during droplet transfer and on the back chemical reactions in the weld pool as the weld pool tries to reestablish equilibrium.


Comparative studies were made of composition variations seen during SMA and SA welding. The results show that there are differences in the electrochemical reactions at slag-metal and plasma-metal interfaces. Conduction at slag-metal interfaces is primarily ionic, and both positive and negative ions are present in the slag. For example, oxygen reactions at the slag-metal interface include oxygen discharge and pickup at the anode and oxygen refining at the cathode:


Slag-Metal Interface



The electrochemical reactions are different at the plasma-metal interface, because only positive ions exist in large concentrations in the plasma. This results in oxygen refining at the anode and oxygen pickup at the cathode:

Plasma-Metal Interface





These reactions show that the absence of negative ions in the hot plasma causes the chemical influence of electrochemical reactions to be in opposite directions at the plasma-metal and the slag-metal interfaces.

The experimental results show further that the welding current and the weld travel speed are both important process variables. The results show that the plasma/metal interface controls the electrochemical transfer of metallic elements, and the slag/metal interface controls the electrochemical transfer of nonmetallic elements such as oxygen and sulfur. The anodic electrochemical reactions include the oxidation of iron and alloy elements at the plasma/metal interface and the discharge and pickup of nonmetallic anions such as oxygen and sulfur through the slag/metal interface. The cathodic electrochemical reactions include the reduction of iron and alloy elements through the plasma/metal interface and the refining of nonmetallic elements through the slag/metal interface. The extent of both anodic and cathodic reactions increased as the welding current increased and as the weld travel speed decreased.

Electric and Magnetic Detection and Characterization of Microstructure Constituents:

Electric and magnetic measurements of weldments may serve as a method to determine carbide types and content in steel, phases in aluminum, hydrogen content in steel and other constituents that influence the performance and service of weldments. This investigation demonstrated that measurements of bulk magnetic properties can quantitatively determine the

precipitation sequence (GP1, GP2, Θ' , and Θ) in aluminum-copper alloys [24B, 25B]. The ability to characterize alloy properties and phase stability through correlations with electromagnetic measurements may allow significant improvements in the nondestructive evaluation of advanced alloy properties and the prediction of service life.

4C. LIST OF ALL PUBLICATIONS AND TECHNICAL REPORTS

1. D. W. Oh, "Use of Surrogate Additions to Achieve Mechanistic Understanding of the Role of Titanium and Boron Contents on the Formation of Acicular Ferrite in Steel Weld Metal", Ph.D. Thesis, T-4065, Colorado School of Mines (1992).
2. R.H. Frost, S. Liu, and D.L. Olson, "Influence of Solidification on Inclusion Formation in Welds", Proc. 3rd International Conference on Trends in Welding Research, June 1-5, 1992, Gatlinburg, TN, ASM, Materials Park, OH, pp. 205-209 (1993).
3. A. Wahid, D.L. Olson, C.E. Cross, and D.K. Matlock, "Corrosion of Weldments", ASM Handbook, 10th Edition, 6, pp. 1065-1069 (1993).
4. D.L. Olson and C.E. Cross, "Friction and Wear in the Mining and Mineral Industries", published in the ASM Metals Handbook, Volume 18: Friction, Lubrication, and Wear Technology, pp. 650-655.
5. J.H. Kim, "The Influence of Electrochemical Reactions on the Chemistry of Direct Current Shielded Metal Arc Welding", Ph.D. Thesis, T-4064, Colorado School of Mines (1993).
6. R.H. Frost, D.L. Olson, and S. Liu, "Influence of Solidification on the Formation of Oxide Inclusions in Steel Weld Metal", Presented at the 74th Annual Conference of the AWS, published abstracts, Houston (1993).
7. K. A. Lindahl, "Alloy Phase Analysis from Measurements of Bulk Electronics and Magnetic Properties", Ph.D. Thesis, T-4028, Colorado School of Mines (1993).
8. D.L. Olson, S. Liu, R.H. Frost, G.R. Edwards, and D.A. Fleming, "Nature and Behavior of Fluxes Used for Welding", ASM Handbook, 10th Edition, 6, pp. 55-63, ASM International, Materials Park, OH (1993).
9. J.W. Allen, D.L. Olson, R.H. Frost, "Exothermically-Assisted Shielded Metal Arc Welding", Published Abstracts, 75th Annual AWS Conference, Philadelphia, PA (1994).
10. J.H. Kim, R.H. Frost, and D.L. Olson, "Electrochemical Oxygen Transfer During Direct Current Arc Welding", accepted by Welding J. (1996).
11. D.W. Oh, D.L. Olson, and R.H. Frost, "The Influence of Zirconium and Boron on Low Carbon Steel Weld Metal Microstructure", J. Eng. for Industry, 116 (1), pp. 26-31 (1994).
12. S.K. Marya, D.L. Olson, and G.R. Edwards, "Scope of Predictive Equations in Welding Metallurgy of Steels", to be published in Proc. of JOM-6, Sixth International Conf. on the Joining of Materials, April 5-7, 1993, pp. 258-265, Helsingor, Denmark (1993), also published in Int. J. for the Joining of Materials, vol. 6 (2X), pp. 73-78 (1994).
13. S. Liu, D.L. Olson, and S. Ibarra, "Pyrometallurgy and Physical Metallurgy of Underwater Wet Welds", Proc. 42nd Australian National Welding Conference (WTIA), 2, paper 25, Melbourne, Australia (1994).
14. S.K. Marya, S. Liu, D.L. Olson, and G.R. Edwards, "Underbead Hardness of Heat-Affected Zones in Steels", Proc. of 1st International Conference on Materials and Manufacturing Technologies, Cluj-Napoca, Romania, May 18-20 (1994).

15. J.W. Allen, "Exothermically-Assisted Shielded Metal Arc Welding", M.S. Thesis, T-4629, Colorado School of Mines (1994).
16. M.I. Onsoien, S. Liu, and D.L. Olson, "Use of Active Shielding Gases to Optimize the Weld Metal Microstructure", Proc. OMAE, vol. III, Materials Engineering, pp. 503-507 (1995).
17. K.A. Lindahl, D.L. Olson, and J.U. Trefny, "Alloy Phase Analysis from Measurements of Bulk Magnetic Properties", Met. Trans. A, pp. (1996).
18. M.I. Onsoien, S. Liu, and D.L. Olson, "Oxygen as a Welding Parameter to Fine Tune Structural Steel Weld Metal Microstructure", Welding J., 75, pp. __, (1996).

4D. LIST OF PARTICIPATING SCIENTIFIC PERSONNEL

1. David L. Olson, Co-Principal Investigator
2. Robert H. Frost, Co-Principal Investigator
3. Jeffrey W. Allen, M.S. Student (completed June 1994)
4. Dong. W. Oh, Ph.D. Student (completed December 1992)
5. Jong H. Kim, Ph.D. Student (completed March 1993)
6. David Fleming, M.S. Student (assisted with review article on welding flux)
7. Wesley Wei Wang, Ph.D. Student
8. Steven Malene, Ph.D. Student
8. Jose Ramirez, Post-Doctoral Scientist

6. BIBLIOGRAPHY

- 1B. D.L. Olson, S. Liu, and G.R. Edwards, "Physical Metallurgy Concerns in the Modeling of Weld Metal Transformations", in *Mathematical Modeling of Welding Phenomena*, edited by H. Cerjak and K.E. Easterling, pp. 89-108, Institute of Materials, London, U.K. (1993).
- 2B. A.C. Hunt, G.R. Edwards, and D.L. Olson, "Developments in Controlling Phase Transformations in Microalloyed Steel Weld Metal", *Proc. International Welding Conference*, January 12-14, New Delhi, 2, pp. 1183-1199, Welding Research Institute, Tiruchivapally, India (1987).
- 3B. D.W. Oh, D.L. Olson, and R.H. Frost, "The Influence of Boron and Titanium on Low Carbon Microalloyed Steel Weld Metals", *Welding Journal*, 69, (4), pp. 151s-158s (1990).
- 4B. D.W. Oh, D.L. Olson, and R.H. Frost, "The Influence of Zirconium and Boron on Low Carbon Steel Weld Metal Microstructure", *J. Eng. for Industry*, 116 (1), pp. 26-31 (1994).
- 5B. O. Grong and D.K. Matlock, "Microstructural Development in Mild and Low-Alloy Steel Weld Metals", *Int. Met. Rev.*, 31, pp. 27-48 (1986).
- 6B. D.W. Oh, D.L. Olson, and R.H. Frost, "Nucleation Mechanisms of Acicular Ferrite in Low-Carbon Steel Weld Metal", *Proc. Symp. Welding and Joining Processes*, ASME Publication, PED, 51, pp. 49-61, Atlanta, GA, December 1-6 (1991), ASME, N.Y., N.Y., Book No. H00684 (1991).
- 7B. D. W. Oh, "Use of Surrogate Additions to Achieve Mechanistic Understanding of the Role of Titanium and Boron Contents on the Formation of Acicular Ferrite in Steel Weld Metal", Ph.D. Thesis, T-4065, Colorado School of Mines (1992).
- 8B. C.W. Ramsay, D.L. Olson, and D.K. Matlock, "The Influence of Inclusions on the Microstructures and Properties of a High Strength Steel Weld Metal", *Proc. Gatlinburg International Conference on "Recent Trends in Welding Research"*, May 14-18, 1989, pp. 763-768, Metals Park, Ohio (1990).
- 9B. S.Liu and D.L. Olson, "The Role of Inclusions in Controlling HSLA Weld Metal Microstructures", *Welding Journal*, 65 (6), pp. 139s-149s (1986).
- 10B. S.Liu and D.L. Olson, "The Influence of Inclusion Chemical Composition on Weld Metal Microstructure", *J. Mat. Eng.*, (9), pp. 237-251 (1987).
- 11B. O. Grong, T.A. Siewert, G.P. Martins, and D.L. Olson, "A Model for the Silicon-Manganese Deoxidization of Steel Weld Metals", *Met. Trans* 17A, (10), pp. 1797-1807 (1986).
- 12B. R.H. Frost, S. Liu, and D.L. Olson, "Pyrochemical Evaluation of Weld Metal Inclusion Evolution", *Proc. 3rd International Conference on Trends in Welding Research*, June 1-5, 1993, Gatlinburg, TN, pp. 205-209, ASM, Materials Park, OH (1993).
- 13B. D.L. Olson, S. Liu, and G.R. Edwards, "Role of Solidification in HSLA Steel Weld Metal Chemistry", *Proc. ASM Weldability of Materials Symposium*, Detroit, MI, October 6-12, pp. 183-190, ASM, Materials Park, OH (1990).

- 14B. R.E. Francis, J.E. Jones, and D.L. Olson, "Effect of Shielding Gas Oxygen Activity on GMA Microalloyed HSLA Steel Weld Metal Microstructure", *Welding Journal*, 69 (11), pp. 408s-415s (1990).
- 15B. D.L. Olson, S. Liu, S. Ibarra, and O. Runnerstam, "Oxygen As A Welding Parameter: The Role of Light Metallography", *Microstructural Science* 20, pp. 31-44, (1993).
- 16B. M.I. Onsoien, S. Liu, and D.L. Olson, "Use of Active Shielding Gases to Optimize the Weld Metal Microstructure", *Proc. OMAE*, vol. III, *Materials Engineering*, pp. 503-507 (1995).
- 17B. M.I. Onsoien, S. Liu, and D.L. Olson, "Shielding Gas Oxygen Equivalent in Weld Metal Microstructure Optimization", to be published in *Welding Journal* (1996).
- 18B. J. W. Allen, "Exothermically-Assisted Shielded Metal Arc Welding", M.S. Thesis, T-4629, Colorado School of Mines (1994).
- 19B. M. Blander and D.L. Olson, "Electrochemical Effects on Weld Pool Chemistry In Submerged Arc and DC Electroslag Welding", *Proc. International Conference on Trends in Welding Research*, Gatlinburg, TN, May 19-22, pp. 363-366, ASM Materials Park, OH (1986).
- 20B. J.H. Kim, R.H. Frost, D.L. Olson, and M. Blander, "Electrochemical Reactions at the Electrode in Submerged Arc Welding", *Proc. of Joint International Symposium on Molten Salts*, Honolulu, HI, October 18-23, editors G. Mamantov et al, vol 87-7, pp. 928-938, Electrochemical Society, Inc., Pennington, NJ (1987).
- 21B. J.H. Kim, R.H. Frost, D.L. Olson, and M. Blander, "Effect of Electrochemical Reactions on Submerged Arc Weld Metal Compositions", *Welding Journal*, 69 (12), pp. 446s-453s (1990).
- 22B. J.H. Kim, "The Influence of Electrochemical Reactions on the Chemistry of Direct Current Shielded Metal Arc Welding", Ph.D. Thesis, T-4064, Colorado School of Mines (1993).
- 23B. J.H. Kim, R.H. Frost, and D.L. Olson, "Electrochemical Oxygen Transfer During Direct Current Arc Welding", accepted by *Welding J.* (1996).
- 24B. K. A. Lindahl, D.L. Olson, and J.U. Trefny, "Alloy Phase Analysis from Measurements of Bulk Magnetic Properties", to be published in *Met. Trans* 27A (1996).
- 25B. K. A. Lindahl, "Alloy Phase Analysis from Measurements of Bulk Electronics and Magnetic Properties", Ph.D. Thesis, T-4028, Colorado School of Mines (1993).